




MAXXAM™ NHFR
NON-HALOGEN
FLAME RETARDANT
POLYOLEFINS




Maxxam™ NHFR Polyolefins – Homopolymers

Product Name	H15 H XF V2 70	MF5200-5004 NHFR V2 HS	MF5200-5005 NHFR V2 RS H	MF5200-5006 NHFR V2 RS HS	H6 H XF V0 70	H20 H XF V0 T 70	H6 T/05 H XF V0 70	H6 T/10 H XF V0 70	H6 T/20 XF V0 T 70	H6 GF/10 XF V070	H8 GF/20 XF V0 70	H12 GF/25 H XF V0 70	H6 GF/30 XF V0 70	PE H XF V0 70	
Polymer	PP													PE	
Flammability	V2	V2	V2	V2	V0	V0	V0	V0	V0	V0	V0	V0	V0	V0	
UL Listed	No	No	No	No	No	No	No	No	No	No	No	No	No	Yes	
Reinforcement	Unfilled	Unfilled	Talc	Talc	Unfilled	Unfilled	Talc	Talc	Talc	Glass Filled	Glass Filled	Glass Filled	Glass Filled	Unfilled	
Density (g/cm3)	1.03	0.9	0.98	1.05	1.07	1.06	1.08	1.15	1.16	1.11	1.25	1.32	1.35	1	
MFI, 230°C/2.16 kg	13	20	23	20	5.5	20	6	6	6	6	7	12	5.5		
E-Modulus (Tensile Modulus - Mpa)	1900	1500	2400	2600	2500	2500	2500	3000	3000	4300	6500	7500	8250	2000	
Tensile Strength (Mpa)	25	30	32	30	26	20	26	25	23	55	70	75	78	20	
Elongation (%)	<20	7	7	8	20	6	<20	<15	<10	4	3	3.5	3	<10	
Izod Impact 23°C Notched (%)	2	3.5	4	2	2	1.5	3.5	5	2	5,5	9	8	8.5	8.5	
Flammability @ Wall Thickness	V-2 (1.6 mm)	V-2 (1.6 mm)	V-2 (1.6 mm)	V-2 (1.6 mm)	V-0 (1.6 mm) 5VA (2.0 mm)	V-0 (1.6 mm) 5VA (2.0 mm)	V-0 (1.6 mm)	V-0 (1.6 mm)	V-0 (1.6 mm)	V-0 (1.6 mm)	V-0 (1.6 mm)	V-0 (1.6 mm)	V-0 (1.6 mm)	V-2 (0.8 mm) V-0 (1.6 to 3.2 mm)	V-0 (1.6 mm)
GWFI @ 2mm (°C)	850	850	850	850	960	960	960	960	960	960	960	960	960	960	

Disclaimer: The technical data provided here reflects the characteristic values of flame-retardant polypropylene materials and is not intended as a product specification. Please note that material properties may vary based on factors such as color and processing conditions. Users should independently evaluate the material for its suitability in specific applications.

Maxxam™ NHFR Polyolefins – Copolymers & Homopolymers and Copolymers

Product Name	C10 XF V2 70	C10 H XF V0 70	C10 H XF V0 T	C10 T/10 XF V0 70	C10 T/20 XF V0 70	C6 GF/30 H XF V0 70	C2 GF/20 XF V0 T 70	C6 GF30 H UV XF V0 70	GREY X2 70	GREY X3 70	
Resin Chemistry	COPO								HOMO + COPO		
Polymer	PP										
Flammability	V2	V0	V0	V0	V0	V0	V0	V0	V0	V0	
UL Listed	No	No	No	No	No	Yes	No	No	No	No	
Reinforcement	Unfilled	Unfilled	Unfilled	Talc	Talc	Glass Filled	Glass Filled	Glass Filled	Glass Filled	Glass Filled	
Density (g/cm3)	1.01	1.06	1.09	1.16	1.28	1.35	1.23	1.38	1.24	1.25	
MFI, 230°C/2.16 kg	7	10	10	9	10	4.5		4.5	4	0	
E-Modulus (Tensile Modulus - Mpa)	1800	1500	1300	1500	2400	8000	5000	8000	5250	6000	
Tensile Strength (Mpa)	18	15	20	15	15	60	45	60	40	45	
Tensile Strain at Break (ISO 527-2) (%)	63	<30	<25	10	2	3.5	6	<5	<10	3	
Izod Impact 23°C Notched (%)	4	7	6	7	2.5	10	13	10	10	9	
Flammability @ Wall Thickness	V-2 (1.6 mm)	V-0 (1.6 mm)						V-0 (1.6 mm) 5VA (1.5 mm) 5VA (2.0 mm)		V-0 (1.6 mm) 5VA (2.0 mm)	



Disclaimer: The technical data provided here reflects the characteristic values of flame-retardant polypropylene materials and is not intended as a product specification. Please note that material properties may vary based on factors such as color and processing conditions. Users should independently evaluate the material for its suitability in specific applications.


MAXXAM™ NHFR NON-HALOGEN FLAME RETARDANT POLYOLEFINS

Maxxam™ NHFR Non-Halogen Flame Retardant Polyolefins are designed to meet strict industry flammability standards. Our range includes both standard and custom solutions that comply with UL 94 V-2, V-0, and 5VA ratings, with many grades offer high Relative Thermal Index (RTI) ratings and a Glow Wire Flammability Index (GWFI) up to 960°C.

These formulations are ideal for applications in various industries, including consumer products, electronics, transportation, and industrial equipment. We also provide options for custom formulations using recycled polypropylene (PP) and polyethylene (PE).

KEY CHARACTERISTICS

- UL 94 V-2, V-0, and 5VA ratings
- Elevated RTI ratings and GWFI (IEC 60695-11-10) up to 960°C
- Injection molding and extrusion grades
- Low dielectric performance with selected formulations
- Good recyclability
- Colorable



1.844.4AVIENT
www.avient.com



Copyright © 2025, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.